

# STAUF

— seit 1828 —



## STAUF D 70

Very low emission tile slip stop



### Technical Datasheet


Product number	✓ 141080
Special features	✓ tiles can be exchanged ✓ tile slip stop
Application range	✓ slip stop for self-laying carpet tiles
Suitable for installation of	✓ Self laying carpet tiles
Suitable subfloors	✓ calcium sulphate (flow) floors ✓ Raised access floors ✓ wooden planks, wood fibre boards ✓ STAUF levelling compounds ✓ chipboards V100 (E1), OSB boards ✓ unlaminated gypsum fibre boards ✓ cement floors
Suitable levelling compounds	✓ STAUF XP 40 ✓ STAUF XP 20 ✓ STAUF GS ✓ STAUF GS-Stand ✓ STAUF GS Basic ✓ STAUF FZ ✓ STAUF XP 10 ✓ STAUF RM ✓ STAUF SSP RAPID
Product properties	✓ permanently sticky adhesive film ✓ in homes ✓ suitable on subfloor heating systems ✓ easy to roll out ✓ very economical ✓ low viscosity
Color	✓ white
Required quantities per m <sup>2</sup>	✓ 75g when applied with roller

Open time	✓ 60 - 80 minutes at 20 °C
Flash time	✓ 15 - 30 minutes
Accessibility	✓ immediately
Room climate at work site	✓ minimum 15 °C, maximum 75% rel. humidity, preferably max. 65%
Transport requirements	✓ frost-free
Storage requirements	✓ frost-free
Shelf-life	✓ 9 months
Giscode	✓ D1
Ecode	✓ EC1 plus
Available packaging	✓ 10 kg plastic canister




## EXAMINATION OF SUBFLOOR

Prior to processing, the subfloor must be checked according to the standard DIN 18365 or corresponding national standards (e.g. BS 5325). The subfloor shall be resistant to pressure and tension, free of cracks, must have sufficient surface strength, be permanently dry, level, clean and free of contaminants that may prevent adhesion, sinter layers etc. In addition, porosity and grip of surface need to be checked. Also check moisture content and absorption of subfloors as well as temperature, air humidity and subfloor temperature.



## SUBFLOOR PREPARATION

It must be ensured that the subfloor is ready for installation by performing proper subfloor preparation, floors must be clean, have sufficient surface strength, must be level, permanently dry and free of cracks. A mechanical pretreatment of the subfloor (sweeping, vacuuming, mechanical brushing, sanding, milling, shot blasting) must be performed depending on type and condition of subfloor. Cracks and joints, except expansion joints and other construction joints, shall be solidly closed with STAUF repair resin and floor brackets. Cavities and indentations can be filled with a non self-levelling STAUF levelling compound. Before installing floor coverings, the properly prepared sub floors must normally be levelled using the appropriate STAUF levelling compound. Once sub floors have been levelled, do not apply primers.



## PROCESSING

Apply adhesive evenly on sub floor using appropriate roller. Let adhesive dry until adhesive layers become transparent (15-30 minutes). The higher the applied quantity, the better the adhesion. After specified flash-time and after the adhesive film has become transparent, install floor covering during open time and press down or rub down firmly. With regard to installation, always observe manufacturer's instructions.



## LIMITATION OF LIABILITY

The foregoing representations are based on the results of our most current product and material testing and are of a non-obligatory advisory nature only since we have no control over the actual quality of workmanship, materials used and worksite conditions. As such, they do not constitute an express or implied warranty of any kind. The same applies to our commercial and technical consultation services which are provided free-of-charge and without obligation. Therefore, we strongly recommend that prior on-site testing be conducted to observe and study the suitability of the product for the intended purpose. With the release of this technical information, all prior technical information (technical data sheets, installation recommendations and other information regarding similar purposes) becomes invalid.

**STAUF KLEBSTOFFWERK GMBH** . Oberhausener Str. 1 . 57234 Wilnsdorf . Germany  
Fon: +49 (0) 2739 301-0 . Fax: +49 (0) 2739 301-200 . Email: [info@stauf.de](mailto:info@stauf.de)

19.01.2021 - 17:48:51